

# BASIC

## Product Data

- DECKING
- CLADDING

**Scientific Name:** Pinus Sylvestris

**Family:** Pinaceae

**Origin:** North Europe

**Biological Durability Class:** III



### Intense Thermal Treatment

Density (20/65) [kg/m <sup>3</sup> ]	460
Modulus of rupture (MOR) [MPa]	35
Modulus of elasticity (MOE) [GPa]	8,9
Compressive Strength [MPa]	46
Static Hardness (Janka) [N]	1839

\* Values in parentheses correspond to standard deviation

FSC® or PEFC certified in accordance with EUDR, UKFRC, EPBC ACT, BEL and Lacey Act



Official partner of natural fire retardant solutions



Rot-Resistant



High Dimensional Stability



Longer-Lasting

**ESSENTIAL  
DURABILITY  
AND QUALITY**



The mark of  
responsible forestry  
FSC® C121009

Ask us about our Certified Products

**TIMBRA.**  
**TECH** Innovating Nature  
Building Futures